

## CLAIMS

## WHAT IS CLAIMED IS:

1. A semiconductor device package (50, 102, 110) comprising:
  - a molding compound (54) forming at least a portion of a first package face (56);
  - a semiconductor device (14) at least partially covered by the molding compound (54),
  - 5 the semiconductor device (14) including a plurality of I/O pads (80); and
  - a lead frame (52, 100, 112) of electrically conductive material at least partially covered by the molding compound (54), the lead frame (52, 100, 112) including a plurality of leads (60), each of the leads (60) including:
    - an interposer (64) having opposing first and second ends (66, 68), the interposer
    - 10 (64) being spaced apart from the first package face (56),
    - a board connecting post (70) extending from the interposer (64) proximate the first end (66) and terminating at the first package face (56),
    - a support post (74) spaced apart from the board connecting post (70), the support post (74) extending from the interposer (64) proximate the second end (68) and
    - 15 terminating at the first package face (56), and
    - a bond site (78) formed on a surface of the interposer (64) opposite the support post (74), at least one of the I/O pads (80) being electrically connected to the interposer (64) at the bond site (78).
- 20 2. The semiconductor device package (50, 102) of claim 1, wherein the at least one of the I/O pads (80) is wire bonded or tape bonded to the bond site (78).
3. The semiconductor device package (50, 102) of claim 2, wherein the at least one of the I/O pads (80) is electrically connected to the interposer (64) at the bond site (78) by
- 25 a wire forming a wedge bond at the I/O pad (80) and a wedge bond at the bond site (78).
4. The semiconductor device package (50, 102) of claim 3, wherein the wire is made from aluminum or aluminum base.

30

5. The semiconductor device package (110) of claim 1, wherein the at least one of the I/O pads (80) is directly soldered to the bond site (78) for forming a flip-chip type connection.

35

6. The semiconductor device package (50, 102, 110) of claim 2, wherein the molding compound (54) forms at least a portion of a second package face (58) adjacent to the first package face (56), and a side surface (124) of the board connecting post (70) adjacent an end surface (72) of the board connecting post (70) is visible at the second package face (58).

40

7. The semiconductor device package (50, 102, 110) of claim 6, wherein a corner between the side surface (124) of the board connecting post (70) and the end surface (72) of the board connecting post (124) is removed to form a relief (128), the relief (128) having a height of between about 1 mil to about 2 mils measured from the end surface (72) of the board connecting post (124).

45

8. The semiconductor device package (50, 102, 110) of claim 1, wherein each of the leads (60) is formed from a strip of material having a channel (82) disposed across the strip.

50

9. The semiconductor device package (50, 102, 110) of claim 8, wherein the channel (82) is filled with the molding compound (54).

10. A method of packaging a semiconductor device (14), the method comprising:  
forming a lead frame (52, 100, 112) from electrically conductive material, the lead frame (52, 100, 112) including a plurality of leads (60), each of the leads (60) including:

55

an interposer (64) having opposing first and second ends (66, 68),

a board connecting post (70) extending from the interposer (64) proximate the first end (66), the board connecting post (70) having an end surface (72) distal from the interposer (64),

60

a support post (74) spaced apart from the board connecting post (70) and extending from the interposer (64) proximate the second end (68), the support post (74) having an end surface (76) distal from the interposer (64), and

a bond site (78) formed on a surface of the interposer (70) opposite the support post (74);

supporting the end surfaces (72, 76) of the support post (74) and the board connecting  
65 post (70); and

electrically connecting I/O pads (80) on the semiconductor device (14) to the bond sites  
(78) while supporting the end surfaces (72, 76) of the support post (74) and the board  
connecting post (70); and

covering at least a portion of the semiconductor device (14), and at least a portion of  
70 the lead frame (52, 100, 112) with a molding compound (54) while supporting the end surfaces  
of the support post (74) and the board connecting post (70).

11. The method of claim 10, wherein electrically connecting the I/O pads (80) to the  
bond sites (78) includes:

75 wire bonding or tape bonding each I/O pad (80) to an associated bond site (78).

12. The method of claim 11, wherein the wire bonding each I/O pad (80) to an  
associated bond site (78) includes:

wedge bonding a wire (18) to the I/O pad (80), and  
80 wedge bonding the wire (18) to the bond site (78).

13. The method of claim 12, wherein the wire (18) is made of aluminum or aluminum  
base.

85 14. The method of claim 10, wherein electrically connecting the I/O pads (80) to the  
bond sites (78) includes:

directly electrically connecting the I/O pads (80) to the bond sites (78) to form a flip-  
chip type connection.

90 15. The method of claim 10, wherein supporting the end surfaces (72, 76) of the  
support post (74) and the board connecting post (70) includes:

adhering the end surfaces (72, 76) of the support post (74) and the board connecting  
post (70) to a surface (94).

95 16. The method of claim 10, wherein the molding compound (54) forms at least a  
portion of a first package face (56), and the end surfaces (72, 76) of the support post (74) and  
the bond connecting post (70) are coplanar with the first package face (56).

17. The method of claim 16, wherein the molding compound (54) forms at least a  
100 portion of a second package face (58) adjacent to the first package face (56), and a side surface  
(124) of the board connecting post (70) adjacent the end surface (72) of the board connecting  
post (70) is visible at the second package face (58).

18. The method of claim 17, wherein a corner between the side surface (124) of the  
105 board connecting post (70) and the end surface (72) of the board connecting post (70) is  
removed to form a relief (128), the relief (128) having a height of between about 1 mil to about  
2 mils measured from the end surface (72) of the board connecting post (70).

19. The method of claim 10, wherein forming the lead frame (52, 100, 112) includes:  
110 forming a lead frame precursor from electrically conductive material, the lead frame  
precursor including a plurality of lead precursors, each of the lead precursors being a strip of  
the conductive material; and  
disposing a channel (82) across each of the lead precursors to form the plurality of  
leads (60).

115

20. The method of claim 19, further comprising:  
filling the channel (82) in each lead with the molding compound (54).

21. A semiconductor device package (50, 102, 300) comprising:  
120 a molding compound (54) forming at least a portion of a first package face (56);  
a semiconductor device (14) at least partially covered by the molding compound (54),  
the semiconductor device (14) including a plurality of I/O pads (80); and  
a lead frame (52, 100, 302) of electrically conductive material at least partially covered  
by the molding compound (54), the lead frame (52, 100, 302) including a plurality of leads  
125 (60), each of the leads (60) including a bond site (78) formed thereon, each bond site (78)  
being electrically connected to an associated I/O pad (80) by a wire (18), the wire (18) forming  
a wedge bond at the I/O pad (80) and a wedge bond at the bond site (78).

22. The semiconductor device package (50, 102, 300) of claim 21, wherein the wire  
130 (18) is made from aluminum or aluminum base.

23. The semiconductor device package (50, 102) of claim 21, wherein each of the leads (60) further includes:

135 an interposer (64) having opposing first and second ends (66, 68), the interposer (64) being spaced apart from the first package face (56),

a board connecting post (70) extending from the interposer (64) proximate the first end (66) and terminating at the first package face (56),

140 a support post (74) spaced apart from the board connecting post (70), the support post (74) extending from the interposer (64) proximate the second end (68) and terminating at the first package face (56), the bond site (78) being formed on a surface of the interposer (64) opposite the support post (74).

24. The semiconductor device package (300) of claim 21, wherein the lead frame (302) is etched to separate the leads (60) after the molding compound (54) is applied to the lead  
145 frame (302).

25. The semiconductor device package (50, 102, 300) of claim 21, wherein the wire (18) has a wedge width between about 1.2 to about 1.5 times a diameter of a portion of the wire (18) extending between the I/O pad (80) and the bond site (78).  
150

26. A method of packaging a semiconductor device (14), the method comprising:  
forming a lead frame (52, 100, 302) from electrically conductive material, the lead frame (52, 100, 302) including a plurality of leads (60), each of the leads (60) including a bond site (78) formed thereon;

155 electrically connecting I/O pads (80) on the semiconductor device (14) to the bond sites (78), the electrically connecting including:

wedge bonding a wire (18) to the I/O pad (80), and

wedge bonding the wire (18) to the bond site (78).; and

160 covering at least a portion of the semiconductor device (14), and at least a portion of the lead frame (52, 100, 302) with a molding compound (54).

27. The method of claim 26, wherein the wire (18) is made of aluminum or aluminum base.

165 28. The method of claim 26, wherein each lead includes:

an interposer (64) having opposing first and second ends (66, 68),

a board connecting post (70) extending from the interposer (64) proximate the first end (66), the board connecting post (70) having an end surface (72) distal from the interposer (64),

170 a support post (74) spaced apart from the board connecting post (70) and extending from the interposer (64) proximate the second end (68), the support post (74) having an end surface (76) distal from the interposer (64), the bond site (78) being formed on a surface of the interposer (70) opposite the support post (74), the support post (74) supporting the bond site (78) during the wedge bonding of the wire (18) to the bond site (78).

175 29. The method of claim 26, wherein the wedge bonding includes ultrasonic bonding.

30. The method of claim 26, wherein the wedge bonding includes thermosonic bonding.

180 31. The method of claim 26, wherein the wire (18) is wedge bonded to the I/O pad (80) before the wire (18) is wedge bonded to the bond site (78).

32. The method of claim 26, further comprising:  
etching the lead frame (302) to separate the leads (60) after electrically connecting the  
185 I/O pads (80) on the semiconductor device (14) to the bond sites (78).

33. The method of claim 26, wherein the wire (18) has a wedge width between about 1.2 to about 1.5 times a diameter of a portion of the wire (18) extending between the I/O pad (80) and the bond site (78).

190